

APSELIV 31

1 TO 3 MM THICK, SELF-LEVELLING
TWO-COMPONENT EPOXY COATING
FOR FLOORS IN THE FOOD INDUSTRY



DESCRIPTION

APSELIV 31 is a two-component epoxy formulation suitable for resinous coatings of the self-levelling and/or multi-layer type and/or as a coating with a smooth or non-slip surface appearance, with thicknesses from 1 to 3 mm.

FIELDS OF APPLICATION

APSELIV 31 is used for floor coverings with the following applications:

- Coatings for dairies, oil mills, etc;
- Chemical and pharmaceutical industries;
- Coatings for the food industry;
- Coatings for laboratories, sterile rooms and hospitals;
- Coatings for aseptic rooms.

PACKAGING

Comp. A + B = 5 + 1.5 kg in metal cans
or

Comp. A + B = 16 + 4.8 kg in metal milk

CONSUMPTION

Self-levelling coating (2 mm thick)

0.5 kg/m² APSEPRIMER NS 125

1.5 kg/m² Quartz dusting

1.5 kg/m² APSELIV 31 (A+B)

1.3-1.5 kg/m² Quartz Livel (Charge)

As it is a self-levelling composition, the flatness conditions of the substrate greatly influence consumption.

2. Multilayer coating (1.5 mm thick)

0.7 kg/m² APSEPRIMER NS 125

1.5 kg/m² Quartz dusting

0.8 kg/m² APSELIV 30 (A+B) (RUVIDO)

1.4 kg/m² APSELIV 30 (A+B) (SMOOTH)

MIXING RATIO

The mixing ratio by weight is:

Comp. A : B = 100 : 26

Binder ratio

Binder (A+B) : inert = 12.6 : 6

CHARACTERISTICS AND ADVANTAGES

APSELIV 31 is a two-component, fillerised formulation based on epoxy resins. It is particularly suitable for the food industry. APSELIV 31 can be applied in thicknesses up to 3 mm. APSELIV31 is recommended for environments with medium chemical aggression and severe mechanical stress. Due to its aesthetically pleasing appearance, APSELIV 31 can also be used as a civil or decorative flooring.

APSELIV 31 has the following advantages:

- Good resistance to chemical aggression
- Good resistance to mechanical stress Aesthetically pleasing appearance for use also in civil engineering;
- Operating temperature from -20°C to +60°C.

CERTIFICATIONS

APSELIV 31 complies with UNI EN 13813: materials for screeds (DoP No. 423).

ISO 9001 certified quality management system (Certificate No. IT.17.0227.01.QMS).

APSE S.r.l is an active member of CONPAVIPER



APSELIV 31

1 TO 3 MM THICK, SELF-LEVELLING
TWO-COMPONENT EPOXY COATING
FOR FLOORS IN THE FOOD INDUSTRY



SUBSTRATE PREPARATION

Surfaces must be flat, clean, free of dust, oil, grease, mud, crumbling parts, paintwork and anything that may impair adhesion. Any cracks must be repaired with AP300 FIX filler.

If necessary, heat the room before applying APSELIV 31 so that the substrate also reaches a temperature of 10°C. Before applying APSELIV 31, thoroughly vacuum the dust on the substrate.

Application of the primer APSEPRIMER NS 125

Pour all component B into component A and mix thoroughly until a uniform colour is obtained.

Load the product with QUARTZ LIVEL (0.1-0.5 mm) in a weight ratio of 1:0.8.

Spread the mixture obtained on the surface of the suitably prepared substrate and smooth with a smooth trowel, making sure that the surface is perfectly covered.

Immediately after primer application, it is recommended to dust the surface with fine quartz (0.1-0.5 mm) to improve the adhesion of APSELIV 31.

When the APSEPRIMER NS 125 primer has cured, proceed with the application of APSELIV 31.

PRODUCT PREPARATION

Mix the individual components separately. Pour component B (hardener) into component A (coloured resin) and mix for a few minutes with a drill at low speed until a lump-free and homogeneously coloured mixture is obtained. Still under slow agitation, add the required quantity of QUARZO LIVEL aggregate (0.1-0.5 mm) and mix until a homogeneous mixture is obtained.

METHOD OF APPLICATION

APSELIV 30 can be used as a self-levelling and multi-layer coating.

1. Self-levelling coating (thickness 2-3 mm)

- Properly prepare the substrate by shot-peening and subsequent cleaning of the surface;
- Prime the substrate with APSEPRIMER NS 125, according to the instructions in the paragraph 'Substrate preparation';
- Pour APSELIV 31 over the hardened primer and distribute it evenly with a notched trowel;
- It may be necessary to mark off the areas where APSELIV 31 is to be applied with rulers and self-adhesive strips of suitable thickness;
- It is recommended to spread and level the mortar, and to even it out with a bubble break roller in criss-cross passes to facilitate the escape of air.

2. Multilayer coating (1-2 mm thick)

- Properly prepare the substrate by shot-peening and subsequent cleaning of the surface.
- Prime the substrate with APSEPRIMER NS 125, according to the instructions in the previous paragraph 'Substrate preparation'. When the primer has hardened, apply the layer of APSELIV 31 with a smooth or notched trowel.
- Sow the surface with suitable quartz according to the thickness to be achieved;
- Remove excess quartz that is not anchored;
- Apply the finishing coat of APSELIV 31 with a smooth or notched trowel;
- If necessary, seed again and apply a further finishing coat of APSELIV 31 until the desired thickness is obtained.

Apply the product at temperatures between +5°C and +35°C.

CURING TIME

The curing time of a layer of APSELIV 31 is influenced by the ambient temperature.

For drying and curing times (at 20°C), please refer to the table below.

| | |
|-----------------------|-------------|
| Pot-life | 35 min |
| Setting time | 60 min |
| Dust off | 2-4 hours |
| Walkability | 24-48 hours |
| Heavy carriageability | 7 days |
| Complete hardening | 7-10 days |

APSELIV 31

1 TO 3 MM THICK, SELF-LEVELLING
TWO-COMPONENT EPOXY COATING
FOR FLOORS IN THE FOOD INDUSTRY



WARNINGS

- Do not apply APSELIV 31 on dusty or crumbling substrates;
- Do not apply APSELIV 31 on substrates soiled by oils, grease, etc;
- Do not apply APSELIV 31 on substrates not properly prepared and not treated with APSEPRIMER NS 125;
- Do not expose the mixed product to heat sources;
- Do not apply APSELIV 31 on damp substrates or subject to capillary rising damp;
- Do not dilute APSELIV 31 with solvents or water;
- Do not apply APSELIV 31 outdoors.

CLEANING OF TOOLS

The tools used for the preparation and application of APSELIV 31 (A+B) must be cleaned immediately after use with the epoxy solvent DILUEPOX, after hardening of the product, removal can only be done mechanically.

HEALTH AND SAFETY WARNINGS

For information on safety regulations, hazard statements and precautionary advice, please refer to the latest safety data sheet, by requesting it at: ufficiotecnico@apsebg.it

STORAGE

Shelf life more than 12 months if stored in original packaging, in a dry place and free of moisture. Store at temperatures between +5°C and +35°C. Heat plastic containers in a bain-marie if frost or crystals form.

DISPOSAL

Dispose of contents and/or container in accordance with local regulations.



PRODUCT TECHNICAL DATA

PHYSICAL CHARACTERISTICS (at +20°C)

| FEATURE | STANDARD | RESULT | |
|-----------------|---------------|------------------------|------------------------|
| | | COMP. A | COMP. B |
| Appearance | - | Liquid | Liquid |
| Colour | - | Colored | Transparent |
| Specific weight | EN ISO 2811-1 | 1,50 g/cm ³ | 1,00 g/cm ³ |
| Viscosity | EN 8490 | 2150 cps | 300 cps |

PHYSICAL CHARACTERISTICS OF THE MIXTURE (at +20°C)

| FEATURE | STANDARD | RESULT |
|--|---------------|------------------------|
| Colour | - | Coloured to RAL scale |
| Mixture consistency | - | Dense fluid |
| Specific weight of mixture (A+B) | EN ISO 2811-1 | 1,35 g/cm ³ |
| Specific weight of loaded mixture (A+B+QUARTZ) | EN ISO 2811-1 | 1,50 g/cm ³ |
| Non-volatile substances | EN ISO 3251 | Ca. 99% |

PRODUCT PERFORMANCE ACCORDING TO UNI EN 13813

| FEATURE | STANDARD | RESULT |
|---|---------------|--|
| Compressive strength at 28 days | EN 13892-2 | ≥ 47 N/mm ² |
| Flexural strength at 28 days | EN 13892-2 | ≥ 16 N/mm ² |
| TABER abrasion resistance | EN ISO 5470-1 | < 50 mg |
| (Grinding wheel H22, 1000g, 1000 rpm) | EN ISO 6272 | 20 N.m |
| Impact resistance | EN 13892-8 | >3,1 N/mm ² |
| Grip strength | EN 13036-4 | 66 |
| Slip resistance (dry surface) | UNI 8298-10 | 0,1-1,0 MO 0,03-0,5 MO |
| Surface electrical resistance | EN 13501-1 | 0,002 kg/m ² h ^{0,5} |
| Capillary absorption and water permeability | EN ISO 868 | >85 |
| Shore D hardness | EN 13501-1 | F _{fl} |

CHEMICAL RESISTANCE OF THE PRODUCT IN OPERATION ACCORDING TO EN 13529

| FEATURE | STANDARD | RESULT |
|----------------------|----------|----------------|
| Hydrocarbon mixture | EN 13529 | Class I |
| Sulphuric acid 20 | | Class I and II |
| Sodium hydroxide 20% | | Class I and II |
| Lactic acid | | Class I and II |
| Surfactants | | Class I and II |

The data given above are information obtained from our best technical knowledge, application, and research experience. However, since we are unable to intervene directly in site conditions and work execution, they represent general indications that do not bind APSE S.r.l. in any way. - V&V Group. The information given does not relieve the purchaser of his responsibility to personally test our products as to their suitability with regard to their intended use. The customer is also responsible for verifying that this data sheet is valid for the batch of product of interest to him and is not outdated as superseded by later editions. If in doubt, contact our Technical Department in advance. APSE S.r.l. - V&V Group reserves the right to make technical changes of any kind without prior notice. This revision cancels and supersedes any previous revision, all under the continuous verification of the data according to the new current Standards and our ISO 9001 management system. Please feel free to check the most up-to-date version of this Data Sheet on our website: www.apse.it

